ON Semiconductor®



Final Product/Process Change Notification Document # : FPCN22138X Issue Date: 7 May 2019

Title of Change:	Hydrazine elimination of ON Semiconductor Niigata Co., Ltd. (OSNC) and change to copper wire material in OSPI Carmona.			
Proposed first ship date:	14 August 2019			
Contact information:	Contact your local ON Semiconductor Sales Office or <yukio.kudo@onsemi.com></yukio.kudo@onsemi.com>			
Samples:	Contact your local ON Semiconductor Sales Office or < <u>PCN.samples@onsemi.com</u> > Sample requests are to be submitted no later than 30 days from the date of first notification, Initial PCN or Final PCN, for this change. Samples delivery timing will be subject to request date, sample quantity and special customer packing/label requirements.			
Additional Reliability Data:	Contact your local ON Semiconductor Sales Office or <masahiro.ono@onsemi.com></masahiro.ono@onsemi.com>			
Type of notification:	This is a Final Product/Process Change Notification (FPCN) sent to customers. FPCNs are issued 90 days prior to implementation of the change. ON Semiconductor will consider this change accepted, unless an inquiry is made in writing within 30 days of delivery of this notice. To do so, contact < <u>PCN.Support@onsemi.com></u>			
Change Part Identification:	Date Code			
Change Category:	✓ Wafer Fab Change ✓ Assembly Change	Test Change Other		
Change Sub-Category(s):				
	Before Change Description	After Change Description		
Fab (ONSC)	N1 Fab(Minimum rule=0.8um,Class=10)	N1 Fab (Minimum rule=0.8um, Class=10) AND N2 Fab (Minimum rule=0.25um, Class=1)		
Wire material	Aluminum (without Anti-reflected Layer)	Aluminium (with Anti-reflected Layer)		
Interlayer material	Silicon nitride and Polyimide or Polyimide	Silicon nitride and Silicon oxide or Oxide		
Package wire material	Gold wire	Copper wire		
Mold compound	G600	G700		



Reliability Data Summary: For the elimination of Hydrazine

QV DEVICE NAME: <u>LB11870-TRM-E</u> RMS :<u>J 43387</u>

PACKAGE : <u>HSSOP48 (375 mil)</u>

Test	Specification	Condition	Interval	Results
HTOL	JESD22-A108	Tj=150°C, Maximum supply voltage	1008 hrs	0/77
HTSL	JESD22-A103	Ta=150°C	1008 hrs	0/77
TC	JESD22-A104	Ta= -65°C to +150°C	500 сус	0/77
тнв	JESD22-A101	85°C, 85% RH, Recommended supply voltage	1008 hrs	0/77
uHAST	JESD22-A118	130°C, 85% RH, 18.8psig, unbiased	96 hrs	0/77
PC	PC J-STD-020 JESD-A113 MSL 3 @ 260 °C		-	PASS
НВМ	JS001	100pF,1.5kohm, +/-1kV	-	0/3
CDM	JS002	+/-500V	-	0/3

Reliability Data Summary: For the change of Package wire material and mold compound

QV DEVICE NAME: <u>LB1909MC-BH</u> RMS :<u>026378,051033</u> PACKAGE : <u>SOIC10</u>

Test	Specification	Condition	Interval	Results
HTOL	JESD22-A108	Tj=150°C, Maximum supply voltage	1008 hrs	0/77
HTSL	JESD22-A103	Ta= 150°C	1008 hrs	0/77
TC	JESD22-A104	Ta= -65°C to +150°C	500 сус	0/77
THB	JESD22-A101	85°C, 85% RH,Recommended supply voltage	1008 hrs	0/25
uHAST	JESD22-A118	130°C, 85% RH, 18.8psig, unbiased	96 hrs	0/77
PC	J-STD-020 JESD-A113	MSL 1 @ 260 °C	-	PASS

Note: Judgment Criteria are due to the limits of the electrical characteristics in the detail specification.

Electrical Characteristic Summary:

There is no change in the electrical performance. Datasheet specifications remain unchanged.

List of Affected Parts:

Note: Only the standard (off the shelf) part numbers are listed in the parts list. Any custom parts affected by this PCN are shown in the customer specific PCN addendum in the PCN email notification, or on the <u>PCN Customized Portal</u>.

Part Number	Qualification Vehicle
LB1909MC-BH	LB11870-TRM-E

Appendix A: Changed Products

Product	Customer Part Number	Qualification Vehicle
LB1909MC-BH		LB11870-TRM-E